

CLOUD 9 FLAME RETARDANT 8mm

PRODUCT DATASHEET • ISSUE 5 - 23.06.20



FEATURES

- MANUFACTURED IN THE UK TO BS EN 14499
- EXCELLENT THERMAL AND SOUND REDUCTION PROPERTIES
- CONFORMS TO EC MARINE DIRECTIVES
- SUITABLE FOR STRETCH-FIT OR DOUBLESTICK APPLICATIONS

APPLICATIONS

- HEAVY/GENERAL CONTRACT AND DOMESTIC AREAS
- SUITABLE FOR MARINE WORK
- SUITABLE FOR USE UNDER WOODEN FLOORS
- SUITABLE FOR USE OVER UNDERFLOOR HEATING

STANDARD SPECIFICATIONS

CORE	Cloud 9 combustion modified core	
TOP SURFACE	Printed corona treated polymer film	
BOTTOM SURFACE	Corona treated polymer film	
NOMINAL THICKNESS	8.00 mm	
NOMINAL ROLL WEIGHT	20.1 kg	44.3 lb
WEIGHT PER UNIT AREA	1334 g/m ²	39 oz/yd ²
ROLL LENGTH	11.0 m	36.0 ft
ROLL WIDTH	1.37 m	54 in
CORE DENSITY	160 kg/m ³	
PRODUCT DENSITY	167 kg/m ³	

BS EN 14499:2015 TEST RESULTS - UK AND EU STANDARD FOR CARPET UNDERLAYS

END USE CLASSIFICATION	BS EN 14499	HC/U
WORK OF COMPRESSION AFTER 1000 IMPACTS	BS 4098	>130 J/m ²
RETENTION OF WORK OF COMPRESSION	BS 4098	>90 %
LOSS IN THICKNESS AFTER STATIC LOADING	BS 4939 ISO 3416	<5.00 %
LOSS IN THICKNESS AFTER DYNAMIC LOADING	BS ISO 2094 (R05)	<5.00 %
RESISTANCE TO CRACKING	BS EN 14499	Pass

FIRE RESISTANCE TESTS

CONFORMS TO EUROPEAN MARINE EQUIPMENT DIRECTIVE (MED) 2014/90/EU		
MED QUALITY APPROVAL CERTIFICATE - MODULE B		
IMO - FLAMMABILITY TEST	MSC 307 (88) Pt 5	Pass
IMO - MARINE SMOKE & TOXICITY TEST	MSC 307 (88) Pt 2	Pass
HOT METAL NUT TEST	BS 4790	Pass - Low radius of effect
FRENCH EPIRADIATEUR	NFP 92 -501	Pass Class M3

INDOOR AIR QUALITY TEST

TESTED TO ISO 16000		
FRENCH VOC REGULATIONS	A+	
FRENCH CMR COMPONENTS	Pass	
ITALIAN CAM	Pass	
AgBB/ABG	Pass	
FORMALDEHYDE EMISSION CLASS	E1	
BREEAM® NOR	Compliant	

OTHER RELEVANT TESTS

THERMAL RESISTANCE (TOG RATING)	BS 4745	1.7 Tog
IMPACT SOUND IMPROVEMENT INDEX (TESTED / RATED)	BS EN ISO 10140-3 BS EN ISO 717-2	38 dB

DISCLAIMER

Whilst every effort is made to ensure its accuracy, the data on this sheet is meant for information purposes only. The typical properties listed are the result of extensive laboratory tests, but since Ball & Young has no control over the end use of each material, we cannot guarantee these results are obtained in practice. Users should conduct their own tests to determine the suitability of each material to its intended application.