



CLOUD 9 NIMBUS

- CLOUD 9 APT
- SUITABLE FOR GENERAL DOMESTIC AND LUXURY USE
- EXCELLENT RECOVERY CHARACTERISTICS
- EASY TO LIFT AND HANDLE



RECOMMENDED AREAS OF USE

SUITABLE FOR LUXURY USE AS WELL AS GENERAL DOMESTIC AREAS SUCH AS LIVING ROOMS AND BEDROOMS. SUITABLE FOR WOOD BLOCK FLOORS.

Manufactured in the UK to BS EN 14499:2015

STANDARD SPECIFICATIONS

TOP SURFACE	Printed stitch bonded crepe paper	
BOTTOM SURFACE	White non-woven fabric	
NOMINAL THICKNESS	7.00 mm	
NOMINAL ROLL WEIGHT	12.7 kg	28.0 lb
WEIGHT PER UNIT AREA	843 g/m ²	25 oz/yd ²
ROLL LENGTH	11.0 m	36.0 ft
ROLL WIDTH	1.37 m	54 in
GUARANTEE	Lifetime of the initial carpet installation (when used in recommended areas)	
CORE DENSITY	100 kg/m ³	
PRODUCT DENSITY	116 kg/m ³	

BS EN 14499:2015 TEST RESULTS - UK and EU STANDARD for CARPET UNDERLAYS

END USE CLASSIFICATION	BS EN 14499	GD/U - L/U
WORK OF COMPRESSION AFTER 1000 IMPACTS	BS 4098	>110 J/m ²
RETENTION OF WORK OF COMPRESSION	BS 4098	>80 %
LOSS IN THICKNESS AFTER STATIC LOADING	BS 4939 ISO 3416	<5.00 %
LOSS IN THICKNESS AFTER DYNAMIC LOADING	BS ISO 2094 (R05)	<5.00 %
RESISTANCE TO CRACKING	BS EN 14499	Pass

INDOOR AIR QUALITY TEST

TESTED TO ISO16000		
EUROFINS INDOOR AIR COMFORT ® STANDARD		Pass
EUROFINS INDOOR AIR COMFORT GOLD ® STANDARD		Pass
FRENCH VOC REGULATIONS		A+
FRENCH CMR COMPONENTS		Pass
ITALIAN CAM		Pass
AgBB/ABG		Pass
FORMALDEHYDE EMISSION CLASS		E1
BREEAM INTERNATIONAL		Compliant
LEED v4 (Outside U.S.)		Compliant
BREEAM ® NOR		Compliant



OTHER RELEVANT TESTS

THERMAL RESISTANCE (TOG RATING)	BS 4745	1.9 TOG
IMPACT SOUND IMPROVEMENT INDEX (Test/Rated)	BS EN ISO 10140-3 BS EN ISO 717-2)	34 dB

ISSUE 6 25 AUG-20

CLOUD 9 NIMBUS