



## CLOUD 9 NIMBUS

- CLOUD 9 APT
- SUITABLE FOR GENERAL DOMESTIC AND LUXURY USE
- EXCELLENT RECOVERY CHARACTERISTICS
- EASY TO LIFT AND HANDLE

### RECOMMENDED AREAS OF USE

SUITABLE FOR LUXURY USE AS WELL AS GENERAL DOMESTIC AREAS SUCH AS LIVING ROOMS AND BEDROOMS. SUITABLE FOR WOOD BLOCK FLOORS.

BS EN 14499:2015

### STANDARD SPECIFICATIONS

TOP SURFACE	Printed stitch bonded crepe paper	
BOTTOM SURFACE	White non-woven fabric	
NOMINAL THICKNESS	7.00 mm	
NOMINAL ROLL WEIGHT	12.7 Kg	28.0 lb
WEIGHT PER UNIT AREA	843 g/M <sup>2</sup>	25 oz/yd <sup>2</sup>
ROLL LENGTH	11.0 m	36.0 ft
ROLL WIDTH	1.37 m	54 in
GUARANTEE	Lifetime of the initial carpet installation (when used in recommended areas)	
CORE DENSITY	100 Kg/M <sup>3</sup>	
PRODUCT DENSITY	116 Kg/M <sup>3</sup>	

### BS. 5808 : 1991 TEST RESULTS - BRITISH STANDARD FOR CARPET UNDERLAYS

END USE CLASSIFICATION	BS EN 14499	GD/U - L/U
WORK OF COMPRESSION AFTER 1000 IMPACTS	BS 4098	>110 J/m <sup>2</sup>
RETENTION OF WORK OF COMPRESSION	BS 4098	>80 %
LOSS IN THICKNESS AFTER STATIC LOADING	BS 4939 ISO 3416	<5.00 %
LOSS IN THICKNESS AFTER DYNAMIC LOADING	BS ISO 2094 (R05)	<5.00 %
RESISTANCE TO CRACKING	BS EN 14499	Pass

### INDOOR AIR QUALITY TEST

TESTED TO ISO16000		
EUROFINS INDOOR AIR COMFORT ® STANDARD		Pass
EUROFINS INDOOR AIR COMFORT GOLD ® STANDARD		Pass
FRENCH VOC REGULATIONS		A+
FRENCH CMR COMPONENTS		Pass
ITALIAN CAM		Pass
AgBB/ABG		Pass
FORMALDEHYDE EMISSION CLASS		E1
BREEAM INTERNATIONAL		Compliant
LEED v4 (Outside U.S.)		Compliant
BREEAM ® NOR		Compliant



### OTHER RELEVANT TESTS

THERMAL RESISTANCE (TOG RATING)	BS 4745	1.9 TOG
IMPACT SOUND IMPROVEMENT INDEX (Test/Rated to BS EN ISO 140-8 / BS EN ISO 717-2)		34dB

ISSUE 6 25 AUG-20